



TECHNICAL DATA SHEET - PROTECTIVE FILM

BODYFENCEM

BODYFENCEM is a transparent, adhesive-coated film, specially developed for protecting car bodywork. Its excellent shock-absorbing properties protect your bodywork against chips caused by stones, insects, car doors, washing brushes, etc. Improved surface sliding. Matt surface finish.

FILM FEATURES:

	Inc	licati	ve v	<u>ralue</u>
--	-----	--------	------	--------------

Total thickness (film + adhesive) (µm): 180 ±10 %

Average values Standard

Tensile strength (N/25 mm): > 100 HEXNFX41021

Elongation at break (%):
> 350
HEXNFX41021

Shrinkage 168 hours at 70 °C (158 °F) (mm): < 0.2 HEXRET001

LINER:

Silicone-coated PET liner.

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

nea	sured average values at publication of the technical of t	verage values	<u>Standard</u>
•	Peel strength test 180° (N/25 mm): after 20 minutes of application: after 24 hours of application:	2 I 23	HEXFTM001
•	Initial tack (N/25 mm):	12	HEXFTM009
•	Release (N/25 mm):	0.3	HEXFTM003

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate and permanent adhesion, optimal after 24 hours of contact.

USER'S INSTRUCTIONS:

• The BODYFENCEM film is intended for vehicle car body protection. It can also serve as a protection system for full wrap films (HX20000, non-structured HX30000 and HX30SCH00) that are used for smooth and basic full wraps without embellishment.

The application of BODYFENCEM to full wrap films is at the customer's judgement. HEXIS recommend the use of pre-cut BODYFENCEM for this particular application. As the adhesion of BODYFENCE is permanent, its removal from a full wrap film can damage the latter. HEXIS decline any responsibility in the case of deterioration of a full wrap film caused by the application and removal of BODYFENCEM.

- Minimum recommended application temperature +10 $^{\circ}$ C (+50 $^{\circ}$ F). Apply preferably between +15 $^{\circ}$ C and +35 $^{\circ}$ C (59 $^{\circ}$ F to 95 $^{\circ}$ F).
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F).
- Cut the film to the size of the part to be wrapped, allowing +10 cm (4 in.) of extra margin.

The remaining film must be stored on its original core (do not cut the rolls into several lengths or widths, do not repackage the product); the roll must be closed immediately and properly (tape or roll-collars) after use in order to preserve all its qualities.

- Apply wet.
- Apply to a surface that is clean and free from any traces of contaminants (dust, grease, wax, silicone, etc.).

Particular care must be taken to clean the angles and periphery of the target surfaces in order to enable the film to adhere properly to the surface.

• In the case of an already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

- Conformable product developed for protecting painted bodywork, underbody, bumpers and rear-view mirror casings, against chips caused by stones, insects.
- Excellent protection against vandalism (key scratches).
- The improved surface slickness of the BODYFENCEM film enables you to reduce squeegee friction during application, but also facilitates the film cleaning.
- To facilitate application, HEXIS have several types of squeegees in its range of accessories, ranging from softer to harder (plastic or felt).
- For more information on the application method of BODYFENCEM, please refer to the Application Guide on the "Professionals" pages, category "Solar and safety films" on our site www.hexis-graphics.com.

STORAGE:

• Shelf life (before application):

The shelf life of this film is I year when stored upright in its original packaging in a dust-free environment at a temperature ranging from +15 °C to +25 °C (+59 °F to +77 °F) with relative humidity of 50 %.

DURABILITY:

• Lifespan depends on the type of substrate, substrate preparation, exposure conditions and nature and frequency of the cleaning.

For instance, it is estimated that a south-facing exposure will divide the durability by two. The same applies to a horizontal exposure. In addition, elevated temperatures (above 50 °C) (+122 °F) or pollution significantly reduce this durability.

• Vertical exposure, North Central European climate:

Up to 7 years (under normal road use conditions). 10-years WARRANTY FOR CERTIFIED INSTALLERS.

Refer to the warranty conditions given in the BODYFENCE warranty document (AMC.DOC.35) available on our website www.bodyfence.net/solutions/warranty/.

Applied to a full wrap film with a durability of less than 7 years, BODYFENCEM will increase the durability against yellowing and cracking of the full wrap film by up to 1 year (within the limit of the BODYFENCEM durability).

NOTES